

Bath solder with suspension eye Sn63Pb37P, 4 kg



with phosphorus content for reduced dross formation

Item no.	WL30067
Model	Sn63Pb37P (Phosphor)
Manufacturer	TAMURA ELSOLD
Manufacturer article no.	STALOT0129
GPSR manufacturer data	TAMURA DEUTSCHLAND GmbH Hüttenstraße 1 DE-38871 Ilsenburg www.tamura-elsold.de
Sales unit	1 kg
Content unit	1 kg

Detail content unit	4 kg
Incl. battery	no
Version (solder bath alloy)	4 kg ingot with suspension eyelet
Recommended solder bath temperature	240 – 260 °C
Melting range	183 °C
Alloy	Sn63Pb37P
Lead-free/lead-containing	containing lead