

Badlot-LF Sn96.5Ag3Cu0.5 MA-S, 200g



- Micro alloy MA-S for reduced dross formation
 - Dimensions: 8 x 10 x 400 mm
- [<https://www.tamura-elsold.de/index.php/en/downloads/safety-data-sheets-sds>Please download here the suitable safety data sheet]

item number	WL30178
model	Sn96,5Ag3Cu0,5 MA-S
manufacturer	TAMURA ELSOLD
manufacturer item number	STALOT0046
order unit	1 kg
content unit	1 kg
detail content unit	200 g

Products for the electronic industry



version ingot	200 g triangular bars
recommended soldering bath temperature	255 – 285 °C
melting range	217 – 219 °C
alloy	Sn96,5Ag3Cu0,5
lead free/containing lead	lead free