

Badlot-LF SnAgCu, 3kg rods



Item no.	WL30532
Model	Sn95,8Ag3,5Cu0,7
Manufacturer	TAMURA ELSOLD
Manufacturer article no.	STALOT0386
GPSR manufacturer data	TAMURA DEUTSCHLAND GmbH Hüttenstraße 1 DE-38871 Ilseburg www.tamura-elsold.de
Sales unit	1 kg
Content unit	1 kg
Detail content unit	3 kg
Incl. battery	no
Version (solder bath alloy)	3 kg ingot with suspension eyelet

Products for the electronic industry



Recommended solder bath temperature	255 – 285 °C
Melting range	221 – 232 °C
Alloy	Sn95,8Ag3,5Cu0,7
Lead-free/lead-containing	lead free

