

Badlot-LF Sn96.5Ag3Cu0.5 MA-S, 1 kg



Afmetingen: 20 x 20 x 355 mm

Artikelnr.	WL30636
Model	Sn96,5Ag3Cu0,5 MA-S
Fabrikant	TAMURA ELSOLD
Fabrikant artikelnr.	STALOT0048
GPSR-fabrikantgegevens	TAMURA DEUTSCHLAND GmbH Hüttenstraße 1 DE-38871 Ilsenburg www.tamura-elsold.de
Verkoopeenheid	1 kg
Inhoudseenheid	1 kg
Gedetailleerde inhoudseenheid	1 kg
Incl. batterij	nee

Products for the electronic industry



Uitvoering (soldeerbadlegering)	1 kg staven
Aanbevolen soldeerbadtemperatuur	255 – 285 °C
Smeltbereik	217 – 219 °C
Legering	Sn96,5Ag3Cu0,5
Loodvrij/loodhoudend	ongelood

